

INSULATION JUST GOT COOLER

ArmaGel DT

Flexible aerogel insulation blanket for cryogenic and dual-temperature applications

// ASTM C1728 Compliant
// More choice: 5, 10, 15 and 20 mm thicknesses
// Integrated zero-perm vapour barrier
// Flexible at cryogenic temperatures









ArmaGel DT

Aerogel is a remarkable material. Although it is the world's lightest solid material, it is strong enough to stop a bullet in its track, and NASA used it to bring home a piece of comet. Armacell for its part is utilising aerogel technology to produce its ArmaGel blanket product range.

Welcome to the next generation of aerogel insulation technology.

ASTM C1728 compliant. Flexible and bendable. Superior thermal performance. Protection against corrosion under insulation. ArmaGel DT is the reliable solution for cryogenic and dual-temperature applications and is compatible with the Armacell Energy existing product range, giving you the best of both worlds.



Cryogenic



Dual-Temperature



Hydrophobic



CRYOGENIC

CONDITIONS

DOWN TO

<u>-180 / -196 °C</u>



Note

ArmaGel DT is compliant with ASTM C1728 Type IV, Grade 1A with minimum use temperature of -196 °C. For operating temperatures below -180 °C, special attention must be given to the system design and craftsmanship during installation to ensure that the material does not come in contact with liquid oxygen. For further information and support, please contact Technical Services.

YOUR BENEFITS

// Increase coverage

New sizes and more choice. 5, 10, 15, and 20 mm thicknesses available today. A thicker layer gives more insulation coverage per man hour than conventional aerogel insulation.

// Faster installation rates

Cuts easily and conforms to preferred shapes, with less wastage, making it the right fit for installers.

// Increase labour productivity

Product removal is made simple, reducing both downtime and the need to purchase replacement insulation during regular maintenance cycles.

// Superior thermal performance

Offering up to 2 times superior thermal performance versus like-for-like competing insulation products.

// Hydrophobic & CUI mitigation

Repels liquid water helping to keep equipment drier for longer and mitigate corrosion under insulation (CUI).

// Ultra-thin

Equal thermal performance at a fraction of the thickness. Improved handling and easier transportation.

// Versatile

More flexibility than conventional aerogel insulation materials.

// Environmentally safe


Dispose of in accordance with local regulations.

// Less waste

ArmGel DT comes in sheet form. It is flexible and more forgiving. It does not crack and can be fabricated to fit any pipe size with minimum waste.

// Acoustic performance

ArmaGel DT offers superior acoustic insertion loss at reduced thickness and weight compared to conventional acoustic insulation systems.



TECHNICAL DATA - ARMAGEL DT

Brief description			ole aerogel ir rmaGel DT is					foil, suitable	for applicati	ons in cryogenic and dual-		
Product colour range	Grey											
Special features	ArmaGel D product is	°F) and +250 °C (+482 °F). Th										
Product range	Sheets in r product ra	ils, please refer to the										
Applications	industrial a	Thermal insulation/protection of pipes, vessels and ducts (including elbows, fittings, flanges etc.) in cryogenic, onsho industrial and process equipment facilities. ArmaGel DT is also used as a component of ArmaSound Industrial System acoustic insulation on industrial pipework and vessels, ensuring reduction of sound transmission.										
Installation	For industrial applications it is recommended to consult the relevant Armacell application manual(s). For further info contact our Technical Services.											
Approvals and compliance												
Approvals, certifications and compliances	Directiv	ant with Mo ve 2014/90/ ed by Burea	'EU.									
Property	Value / Assessment								Standard / Test method			
Temperature range												
Service temperature ¹	Min. °C		Min. °F	Min. °F		Max. °C		Max. °F	ASTM C411			
	-180		-292		25	250		482				
Thermal conductivity												
Declared thermal conductivity ²	θm	-129°C (-200°F)	-73.3°C (-100°F)	-17.8°C (0°F)	23.9°C (75°F)	37.8°C (100°F)	93.3°C (200°F)	149°C (300°F)	204°C (400°F)	ASTM C177		
	λd ≼ [W/ [m⋅K]]	0.015	0.017	0.020	0.021	0.022	0.023	0.025	0.029	_		
	k ≤ [Btu-in, (h-ft²-°F)]	0.10	0.12	0.14	0.14	0.15	0.16	0.17	0.20			
Temperature resistance												
Linear shrinkage under soaking heat	< 2% in widt	< 2% in width and length										
Fire Performance and Approvals	5											
Surface burning characteristics		< 25 Flame Spread Index < 50 Smoke Developed Index								ASTM E84		
Surface flammability	Compliant t	o IMO Part	5							IMO 2010 FTP Code, Part 5		
Smoke generation and toxicity test	Compliant to	Compliant to IMO Part 2							IMO 2010 FTP Code, Part 2			
Resistance to water vapour												
Water vapour sorption	< 5% by weight								ASTM C1104			
Water vapour permeance of integrated vapour barrier	0.00 perm									ASTM E96		
Resistance to water												
Hydrophobic	Yes											
Water absorption	≤ 8% by wei	ght								ASTM C1763		
Corrosion mitigation												
Corrosiveness to steel	Passed, Ma	ss Loss Cor	rosion Rate	(MLCR) not	exceeding th	at of 5 ppm	chloride solu	tion on carb	on steel coup	oon ASTM C1617, Procedure A		

Property	Value / Assessment	Standard / Test method ASTM C692, ASTM C795	
Stress corrosion cracking	Passed		
Physical attributes			
Nominal density	185 kg/m³ (11.5 lb/ft³)	ASTM C303	
Mechanical properties			
Compressive strength ³	rength ³ ≥ 5 psi/ 34.5 kPa at 10% compression At		
Flexibility of insulation blankets	Flexible	ASTM C1101	
Weather and UV resistance			
Weather resistance	In all industrial applications the outer layer of the material must be protected with an adequate covering like metal jacketing or preformed UV-cured GRP (Glass-Reinforced Plastic) cladding. Please contact Technical Services for guidance on the temperature limitations and specific construction considerations which need to be made for each jacketing system.		
Health and environment			
Fungal growth	No growth	ASTM C1338	
Health aspects	Neutral		
Other technical features			
Shelf life ⁴	Max. 3 years		
Storage	Material shall be stored indoors, in clean and dry conditions, away from direct sunlight.		

oxygen. For further information and support, please contact Technical Services. ² Measured under a load of 1.5 kPa (0.22 psi).

³Test performed with a preload of 13.8 kPa (2 psi).

Ashelf life (maximum by border to be storage to be storage of the product and does not affect the lifetime of product after it has been installed.

Roll – standard precovered

ltem	Thickness [mm]	Thickness [Inch]	Width (m)	Width [inch]	Length [m]	Length [ft]	Content [metric]	Content [imperial]		
AGD-05-00/150S	5	0.2	1.5	59	13	42.7	19.5 m ²	209.9 ft ²		
AGD-10-00/150S	10	0.4	1.5	59	8	26.2	12 m ²	129.2 ft ²		
AGD-15-00/150S	15	0.6	1.5	59	5.2	17.1	7.8 m ²	84 ft²		
AGD-20-00/150S	20	0.8	1.5	59	4	13.1	6 m²	64.6 ft²		
Other information										
Thickness toleran	ce	5 mm (0.2 in) nom 10 mm (0.4 in) nor 15 mm (0.6 in) nor 20 mm (0.8 in) nor	ninal thickness ninal thickness	: ± 2.5 mm : ± 3 mm						
Length tolerance		± 5%								
Width tolerance		± 3%								

Roll – jumbo precovered

ltem	Thickness [mm]	Thickness [Inch]	Width (m)	Width [inch]	Length [m]	Length [ft]	Content [metric]	Content [imperial]		
AGD-05-00/150P	5	0.2	1.5	59	80	262.5	120 m ²	1291.7 ft ²		
AGD-10-00/150P	10	0.4	1.5	59	40	131.2	60 m ²	645.8 ft²		
AGD-15-00/150P	15	0.6	1.5	59	26	85.3	39 m ²	419.8 ft ²		
AGD-20-00/150P	20	0.8	1.5	59	20	65.6	30 m ²	322.9 ft ²		
Other information										
Thickness tolerance		5 mm (0.2 in) nominal thickness: ± 1 mm 10 mm (0.4 in) nominal thickness: ± 2.5 mm 15 mm (0.6 in) nominal thickness: ± 3 mm 20 mm (0.8 in) nominal thickness: ± 4 mm								
Length tolerance		± 5%								
Width tolerance		± 3%								

At data and technical information are based on results achieved under the specific continuous defined according to the testing standards referenced. Despite taking every precaution to ensure that said data and technical information are up to date, Armacell does not make any representation or warranty, express or implied, as to the accuracy, content or completeness of said data and technical information. Armacell also does not assume any liability towards any person resulting from the use of said data or technical information. Armacell reserves the right to revoke, modify or amend this document at any moment. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. This document does not constitute nor is part of a legal offer to sell or to contract.

At Armacell, your trust means everything to us, so we want to let you know your rights and make it easier for you to understand what information we collect and why we collect it. If you would like to find out about our processing of your data, please visit our Data Protection Policy.

Trademarks followed by ® or ™ are trademarks of the Armacell Group. © Armacell, 2024. All rights reserved

ArmaGel | ArmaGel DT | Brochure | 052024 | en-VN

ABOUT ARMACELL

As the inventor of flexible foam for equipment insulation and a leading provider of engineered foams, Armacell develops innovative and safe thermal and mechanical solutions that create sustainable value for its customers. Armacell's products significantly contribute to global energy efficiency making a difference around the world every day. With more than 3,300 employees and 25 production plants in 19 countries, the company operates two main businesses, Advanced Insulation and Engineered Foams. Armacell focuses on insulation materials for technical equipment, high-performance foams for acoustic and lightweight applications, recycled PET products, next-generation aerogel technology and passive fire protection systems.



For more information, please visit: www.armacell.com